

	Property	Standard/Norm	Unit	ISO-DRAIN nature 3 P	ISO-DRAIN nature 10 M / 10 MP	ISO-DRAIN nature 10 G / 10 GP	ISO-DRAIN nature 10 GPG	ISO-DRAIN nature 10 G + as	ISO-DRAIN nature 10 GF	ISO-DRAIN nature 20 P	ISO-DRAIN nature 20 PG	ISO-DRAIN nature 25 P
Core Product	Resin	---	---	HDPE	HDPE	HDPE	HDPE	HDPE	HDPE	HDPE	HDPE	HDPE
	Colour	---	---	black	black	black	black	black	black	black	black	black
	Area weight	DIN EN 12127	g/m ²	1,000	600	600	600	600	600	1,000	1,000	1,000
	Dimple height	---	mm	3	10	10	10	10	10	20	20	25
	Dimple spacing	---	pcs/m ²	2,500	3,360	3,360	3,368	3,360	3,360	400	400	400
	Air gap (between dimples)	---	l/m ²	3.6	7.9	7.9	7.9	7.9	7.9	14	14	13.5
	Compressive strength	EN ISO 25619-2	kN/m ²	1,600	420	420	420	420	420	240	240	180
	Dimensions	---	m	1.00 x 2.20 1.00 x 30.00 2.00 x 30.00	2.00 x 12.50 --- ---	2.00 x 12.50 --- ---	2.00 x 12.50 --- ---	2.00 x 12.50 --- ---	2.00 x 12.50 --- ---	1.20 x 2.50 2.00 x 20.00 2.50 x 20.00	2.00 x 12.50 --- ---	1.20 x 2.50 --- ---
	Water storage capacity	---	l/m ²	---	---	---	1.9	---	---	6	6	8
	Perforation	---	mm	2 x 9	--- / 2 x 9	--- / 2 x 9	2 x 9	---	---	5	2 x 9	5
Lamination 1	Resin	---	---	---	PE	PP	PP	PP	PP	---	---	---
	Area weight	DIN EN 12127	g/m ²	---	95	136	136	136	136	---	---	---
Lamination 2	Resin	---	---	---	---	---	PP	---	PE	---	PP	---
	Area weight	DIN EN 12127	g/m ²	---	---	---	136	---	100	---	136	---
Geotextile	Tensile strength	EN ISO 10319	kN/m	---	---	9.0	9.0	9.0	9.0	---	9.0	---
	Puncture (CBR)	EN ISO 12236	N	---	---	1,250	1,250	1,250	1,250	---	1,250	---
	Dynamic cone puncture	EN 918	mm	---	---	29	29	29	29	---	29	---
	Opening size	EN ISO 12956	µm	---	---	120	120	120	120	---	120	---
	Permeability	EN ISO 11058	10 ⁻³ m/s	---	---	50	50	50	50	---	50	---
Geocomposite	Area weight	EN ISO 9864	g/m ²	---	695	740	880	750	840	---	1,140	---
	Drainage capacity	EN ISO 12958, i=1	l/(ms)	0.73	3.0	3.5	3.5	3.5	3.5	10.61	10.61	7.9
	Tensile strength (MD)	EN ISO 10319	kN/m	7.3	26.1	15.4	15.4	15.4	15.4	11.7	16.5	7.1
	Tensile strength (CMD)	EN ISO 10319	kN/m	---	22.2	16.8	16.8	16.8	16.8	11.5	12.4	6.3
	Strain at maximum load	EN ISO 10319	%	40	50	50	50	50	50	55	55	70
	CE Certificate	EN ISO 13252	---	yes	yes	yes	yes	yes	yes	yes	yes	yes
General	Service temperature range	---	°C	-40 - +80								
	Storage	---	---	protect from UV radiation								
	Physiological properties	---	---	resistant to a wide range of chemicals, resistant to fungus and bacteria attack, impervious to root penetration, rot proof								

All figures are to be understood as approximate values. Evaluation of suitability for any specific application is always the sole responsibility of the customer.