



Technical Data

ROOFMATE™ LG-XP

Properties	Standard	Unit	ROOFMATE™ LG-XP	CE-Code
Declared Thermal Conductivity : λ_D	NF EN 13164	W/(m.K)	0.029	λ_D
Compressive stress or compressive strength at 10% deformation ¹⁾	EN 826	kPa	300	CS(10\Y)i
Dimensional stability under specific temperature and humidity conditions	EN 1604	%	<=5	DS(70,90)
Reaction to Fire - Euroclass	EN 13501-1	–	E	–
Dimensions Length x Width Thickness	EN 823 EN 822	mm mm	1250x600 T1	– --
Edge profile	–	–	Long side: Tongue & groove Short side: Butt egde	–
Surface	–	–	Top surface : Mortar layer (10mm)	–

Janvier 2019

Note: The information and data contained in this technical data sheet do not represent exact sales specifications. The features of the products mentioned may vary. The information contained in this document has been provided in good faith, however it does not imply any liability, guarantee or assurance of product performance. It is the purchaser's responsibility to determine whether these Dow products are suitable for the application desired and to ensure that the site of work and method of application conform with current legislation. No licence is hereby granted for the use of patents or other industrial or intellectual property rights. If Dow products are purchased, we advise following the most up-to-date suggestions and recommendations

Product Information:

www.ravatherm.com